

# Masonry Sand

**Sieve:** *ASTM C144*

<b>Size</b>	<b>% Passing</b>
#4	100
#8	95-100
#16	70-100
#30	40-75
#50	10-35
#100	2-15
#200	<5.0

**General Quality Results:**

Bulk Specific Gravity Oven Dry	ASTM C128	2.63
Bulk Specific Gravity SSD	ASTM C128	2.65
Apparent Specific Gravity	ASTM C128	2.68
Absorption %	ASTM C128	0.7

**Available Locations:**

Bromley Lakes  
14585 Brighton Road  
Brighton, Co 80601

**Contact Information:**

Wade Raitz, Sales Representative

[wade.raitz@boral.com](mailto:wade.raitz@boral.com)

Cell: 303-638-3598